

CEFATEX PE

material: 100% PES knitwear

procedure: padding

tests: hydrophilic properties
antistatic effect
elasticity

		<i>unfinished</i>	<i>20 g/l CEFATEX PE</i>	<i>40 g/l CEFATEX PE</i>
hydrophilic properties	sinking time of 1 cm ² piece of fabric in water (sec)	>300	0	0
antistatic effect	electric resistance (Ω)	1x10 ¹¹	8x10 ⁹	8x10 ⁹
elasticity			improved	improved

CEFATEX PE


Soil release properties

mustard


before washing



after washing




unfinished



40 g/l CEFATEX PE

tea


before washing



after washing



unfinished



40 g/l CEFATEX PE